



Used to coat mineral fibre insulation batts already in-situ.

Description

Trowel grade or brush grade, medium viscosity paste, or low viscosity liquid containing acrylic emulsion, inert fillers and fungicide. To be used for internal applications only.

Sizes and Colours

Availability:

Intumastic Brush - 5 litre tubs
Intumastic Trowel - 10 litre tubs

Colour: white. Other colours available to special order.

Can be over-painted

Fire Testing

- In conjunction with a good quality mineral fibre batt system of a minimum density of 140 kg/m³, Intumastic Trowel can provide up to 4 hrs fire integrity to BS 476 Pt 20, BS EN 1366/3-4 depending on specification.

Applications

A mastic used to coat plain mineral fibre batts of a density exceeding 64 kg/m³ in situations where it is more cost effective to install uncoated mineral fibre and later apply.

Installation

1. Read Firetherm Intumastic safety data sheet instructions before starting work.
2. Carefully check that all mineral is securely positioned and tight, with any gaps over 5mm being filled with off cuts of mineral fibre.
3. Mask around the opening with masking tape allowing a margin of at least 25 mm to provide a neat well sealed edge.
4. Firetherm Intumastic may be applied by spray, brush or trowel. Different specifications of Intumastic can be supplied in order to help you achieve the best results.
5. Apply to a loading of approximately 1.3 litres per m² to a wet film thickness of 1.3 mm and a dry film thickness of 1 mm.
6. For bare metal surfaces (such as copper or aluminium), we recommend a barrier tape, masking tape or similar is applied before filling the hole with mastic.
7. If difficulty is experienced in obtaining adhesion, it is good practice to moisten the mineral fibre before applying the Intumastic with a water sprayer or a paint brush dipped in water.
8. Remove masking tape.

Allow Intumastic to dry for at least 24 hours at temperatures higher than 10°C and less than 75% RH before being exposed to moisture.

Tack free time: 30 to 120 minutes depending on temperature, humidity and air movement.

Legislation

Compartment walls and floors must maintain the appropriate level of fire resistance as laid down by Building Regulations Section B 2000. In conjunction with a good quality mineral fibre batt system of a minimum density of 140kg/m³, Intumastic Trowel/Brush can provide up to 4 hours fire integrity to BS 476 Pt 20 and BS EN 1366/3-4, depending on specification.

Firetherm Intumescent & Insulation Supplies Limited
Unit F Acorn Industrial Park, Crayford Road, Crayford, Kent DA1 4FT
Phone: 01322 551010 Fax: 01322 552727 Email: sales@firetherm.com www.firetherm.com

